



KERANATURE TECHNICAL DATA SHEET

Description of the item : KERANATURE MB-MOLDBLEND

Characteristics	Method	Specifications
Melting point, °C	ASTM D87	52 - 58
Oil content, %	ASTM D721	0.75 max
Penetration at 25°C, 1/10 mm	ASTM D1321	20 max
Viscosity at 100°C, CST		2.5 - 4.5
Saybolt colour		+28 min

The values listed in this analysis sheet are derived from our quality control.

This information represents only the general characteristics of the product and should not be interpreted as representing express guarantees regarding the product.

They do not exempt the customer from inspecting incoming materials and testing them for a specific application. The values indicated refer to the day on which they were determined. This document is valid without signature.

Active

Distribution

Company

Telephone: +33 (0) 4 75 54 35
05

Email: contact@adc-solution.com

SIREN: 432 961 134 SIRET: 432 961 134 00041

40 Impasse des Joncs D 126 route d'Allan 26780 Malataverne

ADC France with capital of €163,200 – RCS 432 961 134 VALENCE – VAT FR 64 432 961 134